

Article number:

EGS: 14451

Page: 1/2

Technical Data Sheet

PRODUCT DESCRIPTION:

High-pressure decorative laminates. They feature an attractive and aesthetic appearance, high mechanical strength, durability and resistance to impact, abrasion and scratch, good dimensional stability, resistance to water, steam, hot and cold temperatures, do not corrode. The boards have a black core color. Decors with UV protective film on one side: 0162 BS, 0164 BS, 0171 BS, 0190 BS.

Available in dimensions:

- thickness: 6,0 mm,
 - size: 2800 x 1300 mm; 3050 x 1300mm.
-

APPLICATION:

KronoCompact EGS MPB board can be used as an independent structure in the construction industry.

Construction board for indoor vertical use.

Typical usage:

- Shop fittings
 - DIY applications (indoor)
 - Interior wall covers, partitional walls, bookshelves, school and office furnitures
 - Wall cladding, cubicles, locker, doors, cabinets.
-

STORAGE:

Compact boards should be stored in a dry and roofed placing, at temperatures of 15-25°C, relative humidity of 50%, min. 1,5m distance to source of heat. Keeping in humid conditions with water on the surface might lead to bending Compact boards what should be avoided.

It is recommended to store in the original Kronospan packaging, on pallets. In the case of foiled boards, the foil should be removed immediately after assembly.

Article number:

EGS: 14451

Page: 2/2

Technical Data Sheet

PROPERTIES:

Parameter	Unit	Standard	Requirements
Thickness	mm	438-2.5	$6,0 \pm 0,4$
Length	mm	438-2.6	+10/ - 0
Width	mm	438-2.6	+10/ - 0
Flatness	mm/m	438-2.9	≤ 5
Straightness of edges	mm/m	438-2.7	$\leq 1,5$
Squareness	mm/m	438-2.8	$\leq 1,5$
Resistance to impact with large diameter ball	Drop height, [mm]	438-2.21	≥ 1800
Resistance to immersion in boiling water	Mass gain [%]	438-2.12	≤ 2
	Thickness gain [%]		≤ 2
	Appearance, surface rating		Mat finishes ≥ 4
Resistance to water vapour	Appearance, grade	438-2.14	Mat finishes ≥ 4
Resistance to crazing	Appearance, grade	438-2.24	≥ 4
Flexural modulus	Stress, [MPa]	EN ISO 178:2003	≥ 9000
Flexural strength	Stress, [MPa]	EN ISO 178:2003	≥ 80
Tensile strength	Stress, [MPa]	EN ISO 527-2:1996	≥ 60
Density	[g/cm ³]	EN ISO 1183-1:2004	$\geq 1,35$

Additional information:

The contents of this document are for informational purposes only. Possible mistakes are possible. Customers and third parties are obliged to obtain information about Kronospan products and their usage. We strongly recommend the recipient or user of our products to obtain expert advice regarding compliance with local planning, application requirements, standards, norms etc. Kronospan does not accept any warranties for claims relating to this document.